GlobalDur GN112 Epoxy Primer



TECHNICAL DATA SHEET

Epoxy Primer Solvent Free for Glass and Glazed Concrete

PRODUCT DESCRIPTION

- ♦ GlobalDur GN112EP is an excellent epoxy primer solvent free for glass surfaces (like tiles), hard concrete;
- ♦ GlobalDur GN112EP is specially design to have excellent chemical resistance, mechanical and aesthetic properties;
- GlobalDur GN112EP is a primer specially design for excellent performances on glazed surfaces.

PERFORMANCES

- Excellent adhesion on glass and glazed concrete.
- No harmfull solvents.
- Excellent wet ability to glass and concrete and no dew point restrictions.
- High mechanical properties.

RECOMMENDED USE

PRIMER/INTERMEDIATE/FINISH

OVER CONCRETE

MARINE: Decks, Chain lockers, Tower

bridge, etc.

PROTECTIVE: Over glazed tiles and concrete.

APPROVALS

COMPONENT A	COMPONENT B	COLOURS
GN112EP	H112EP	GN112EPG0000 (Clear).

Physical Properties

GLOSS	Glossy.
SOLIDS BY VOLUME	100 % (theoretical).
VOC*	Max. 90g/Lt.
FLASH POINT	> 100°C (> 212°F) Setaflash
PERFORMANCE	

Application

SURFACE PREPARATION

Painting Direct to Substrate: GlobalDur GN112EP is suitable for concrete surfaces prepared (dry or wet) accordingly with NACE Nº6/SSPC-SP13 using:

Mechanical Surface Preparation Methods.

Chemical Surface Preparation

Flame Cleaning and Blasting

Apart from the surface preparation method, the moisture tolerance of GlobalDur

GN114EpoxiPrimer allow the surface to be washed with tap water and let dry before painting, ensuring a final lower salts level.

Over glass or coated surfaces be sure of the old coating conditions (no coating defects and

ISSUED

Edition 03 / Mod.10 - 01/04/2016

GlobalDur GN112 Epoxy Primer



PERFORMANCE IN COATINGS

corrosion- in "sound conditions") and the compatibility with the GlobalDur GN112EP. Please contact GlobalNavy office in case of any doubt or for further information.

APPLICATION METHOD

CONVENTIONAL METHODS: GN112EP can be applied by brush and roller are suitable. Care should be taken in order to achieve the dft specified. When applying on enclosed areas ensure a good ventilation. It is not necessary to use dehumidification equipment: GlobalDur GN112EP can be applied on dry or on high humidty conditions.

APPLICATION CONDITIONS

The substrate temperature shall be 5°-+50°C. The ambient temperature shall be >5°C. The concrete moisture should be lower than 6% and air humidity lower than 95%.

APPLICATION DATA

GlobalDur GN112 Epoxy Primer is a two pack product, so the base and hardener must be mixed on the right ratio. First, mix well component A during 1 minutes. After that, add all the hardener and stir very well until it get homogeneous. Mix completely both quantities of component A and B packs.

MIX RATIO	3 / 1 (by Weight)	3,7 / 1 (by Volume)
-----------	-------------------	---------------------

HARDENER H112EP

POT LIFE 90 minutes (23°C/73°F).

THINNER N.A.

SOLVENT / CLEANER GN003TH/GN008TH

DRY TIME Surface dry: 8 hours at 23°C (73°F).

Dry to recoat: Min: 16 hours at 23°C (73°F).

Max: 7 days at 23°C (73°F).

THEORETICAL COVERAGE

6.6 m2/Kg (33 Sq.ft/Lb) - Dry/Wet: 0,15 Kg (0,33 pounds)

TYPICAL PAINT SYSTEM

ullet GlobalDur GN112EP 1 x 0,15 Kg (WFT/DFT) + GlobalDur GN32EFSL 1 x 0,3 Kg (DFT) +

GloblThane GN204F 1 x 0,1 Kg (DFT).

This is a system for flooring conditions. Please contact GlobalNavy for other applications.

STORAGE

4 years (storage on the original tightly closed containers in a dry, cool, well ventilated space, at temperatures between 5° C - 40° C).

PACKING

Two pack product available in packs (A+B) 1 Kg, 5Kg and 20 Kg.

FURTHER INFORMATION

The conventional air spray is only possible with a 10% or higher dilution ratio, so it only should be used on special applications - Please contact our GlobalNavy office.

HEALTH SAFETY

Please take the necessary measures in order to accomplish the national laws and regulations regarding the environmental, health and safety at work. Please observe the safety information displayed on the container. Please refer to the Safety Data Sheet for detailed information on the health, safety hazards and precautions for the use of this product.

The information on this data sheet is given to the best of our knowledge based on laboratory testing and practical experience. This is not a specification and all information is given in good faith. Every values presented as Theoretical were calculated from the product formula, so can have deviation from laboratory measurements using standard methods that may be not applicable. However, since the product can be used under conditions beyond our control, the manner of use is the sole responsibility of the user. The product is intended for professional use only. Manufacturer does not assume any liability in connection with the use of the product relative to coverage, performance or injury. This Technical Data Sheet content can be changed without notice.

GlobalDur GN112 Epoxy Primer



PERFORMANCE IN COATINGS

Parque Industrial de Carrascas, Estrada Nacional 252, 2950-402 Palmela PORTUGAL

♦ Tel.:+351 265107979 ♦ www.globalnavy.net ♦ email: sales@globalnavy.net