

# GlobalDur GN126 Epoxy Glassflake



PERFORMANCE IN COATINGS

## TECHNICAL DATA SHEET

### Epoxy Glass Flake Solvent free Moisture Tolerant

<b>PRODUCT DESCRIPTION</b>	◆ GlobalDur GN126EG is an excellent epoxy glassflake/amine two pack anticorrosion primer/intermediate/finish for steel. Can also be applied over concrete. ◆ GlobalDur GN126EG is specially design to have high abrasion resistance. ◆ GlobalDur GN126EG is a primer specially design for excellent anticorrosive performances on high abrasion areas. ◆ GlobalDur GN126EG can be applied as a primer, intermediate or finish (however may have slight colour differences due to its particular properties).	
<b>PERFORMANCES</b>	<ul style="list-style-type: none"><li>• Excellent anticorrosive performance in conjunction with high abrasion resistance;</li><li>• No humidity/dew point restrictions;</li><li>• Excellent resistance to wearing and impact;</li><li>• Excellent adhesion to substrate and between coats;</li><li>• Surface preparation cost reduction;</li><li>• Excellent edge retention.</li></ul>	
<b>RECOMMENDED USE</b>	PRIMER/INTERMEDIATE/FINISH OVER STEEL MARINE: splashzones, decks, underdeck areas, bilge areas, rigs, offshore platforms, etc.. PROTECTIVE: Bridges, pulp industry, chemical industry, machinery, etc..	
<b>APPROVALS</b>	Complies with ISO 12944-5, as being suitable for coating systems until C5-M and Im3.	
<b>COMPONENT A</b>	<b>COMPONENT B</b>	<b>COLOURS</b>
GN126EG	H126EG	GN126EGG7000 (Light Grey), GN126EGG3009 (Red Iron Oxide). For other colours, please contact GlobalNavy's office.

### Physical Properties

<b>GLOSS</b>	Semi gloss.
<b>SOLIDS BY VOLUME</b>	100% (theoretical).
<b>VOC*</b>	<92g/L.
<b>FLASH POINT</b>	100°C (112°F) Setflash.
<b>PERFORMANCE</b>	

### Application

<b>SURFACE PREPARATION</b>	Painting Direct to Substrate: GlobalDur GN126EG, is suitable for surfaces prepared by hydroblasting, grit blasting (dry or wet) and mechanical, accordingly with the following standards: Grit Blasting: SA2 (ISO 8501-1:1988) Hydroblasting: Wj2-M (SSPC SP12 – VIS4(I) / NACE N°5- N°7) Mechanical Means: St3 (ISO 8501-1:1988) Apart from the surface preparation method, the moisture tolerance of GlobalDur
----------------------------	--

<b>ISSUED</b>	Edition 03 / Mod.10 - 21/05/2018
---------------	----------------------------------

# GlobalDur GN126 Epoxy Glassflake



PERFORMANCE IN COATINGS

GN126EpoxyGlassflake allow the surface to be washed with tap water before painting, ensuring a final lower salts level. By this way, it is possible to achieve a non visual standard SC2 (NACE 5 / SSPC-SP12). The rust tolerance of GlobalDur GN126EpoxyGlassflake allow a painting with a flash rust until M degree (standard SSPC VIS4(I) / NACE N°7). The anti corrosive performance over an ST3 surface, followed by degreasing and surface wash is however not so good as the other surface preparation methods. Over coated surfaces be sure of the old coating conditions (no coating defects and corrosion- in "sound conditions") and the compatibility with the GlobalDur GN126EG. However it is always recommended to apply a proper primer to achieve the best performance. Please contact GlobalNavy office in case of any doubt or for further information.

<b>APPLICATION METHOD</b>	SPRAY: Use air-less spray. Use an equipment with a compressing 63:1 ratio, an inlet 4,5 bar pressure, allowing a 240-310 bar outlet pressure. A 0,021" or 0,0 25" tip is recommended. Conventional spray equipment only on special application conditions- contact GlobalNavy for more information. CONVENTIONAL METHODS: Brush and roller are suitable for "stripe-coat" and small areas, care should be taken in order to achieve the dft specified. When applying on enclosed areas ensure a good ventilation. It is not necessary to use dehumidification equipment: GlobalDur GN126EG can be applied on dry or wet surfaces, even with 100% humidity and surface temperatures below the dew point.
<b>APPLICATION CONDITIONS</b>	The substrate temperature shall be 10°-+50°C. The ambient temperature shall be >10°C. There is no dew point restrictions.
<b>APPLICATION DATA</b>	GlobalDur GN126 EpoxyGlassflake is a two pack product, so the base and hardener must be mixed on the right ratio. First, mix well component A during 2 minutes. After that, add all the hardener and stir very well until it get homogeneous. Only if necessary, for na application optimization adjustment, the product can be diluted until 5 % (v/v) with GN001TH. Mix completely both quantities of component A and B packs.
<b>MIX RATIO</b>	5.2 / 1 (by Weight) 4.0 / 1 (by Volume)
<b>HARDENER</b>	H126EG
<b>POT LIFE</b>	45 minutes (23°C).
<b>THINNER</b>	GlobalThin GN001TH.
<b>SOLVENT / CLEANER</b>	GN003TH
<b>DRY TIME</b>	Surface dry: 6 hours at 23°C (73°F) Dry to recoat: Min: 8 hours at 23° C (73°F). Max: 7 days at 23°C (73°F).
<b>THEORETICAL COVERAGE</b>	3.34- 2.00 Sq.m/Lt. (256,4 Sq.ft/US gal - Dry/Wet: 300-500 micron (12-20 mils)
<b>TYPICAL PAINT SYSTEM</b>	• GlobalDur GN101EP 1 x 150µm (dft) • GlobalDur GN126EG 1 x 400µm (dft). This is a system for splash zones conditions. Please contact GlobalNavy for other applications.
<b>STORAGE</b>	4 years (storage on the original tightly closed containers in a dry, cool, well ventilated space, at temperatures between 5°C - 40°C).
<b>PACKING</b>	Two pack product, available in packs (A+B) 5 L and 20 L.
<b>FURTHER INFORMATION</b>	The conventional air spray is only possible with a much higher dilution ratio, so it only should be used on special applications - Please contact our GlobalNavy's office.
<b>HEALTH SAFETY</b>	Please take the necessary measures in order to accomplish the national laws and regulations regarding the environmental, health and safety at work. Please observe the safety information
<b>ISSUED</b>	Edition 03 / Mod.10 - 21/05/2018

# **GlobalDur GN126 Epoxy Glassflake**



PERFORMANCE IN COATINGS

displayed on the container. Please refer to the Safety Data Sheet for detailed information on the health, safety hazards and precautions for the use of this product.

The information on this data sheet is given to the best of our knowledge based on laboratory testing and practical experience. This is not a specification and all information is given in good faith. Every values presented as Theoretical were calculated from the product formula, so can have deviation from laboratory measurements using standard methods that may be not applicable. However, since the product can be used under conditions beyond our control, the manner of use is the sole responsibility of the user. The product is intended for professional use only. Manufacturer does not assume any liability in connection with the use of the product relative to coverage, performance or injury. This Technical Data Sheet content can be changed without notice.

Parque Industrial de Carrascas, Estrada Nacional 252, 2950-402 Palmela PORTUGAL  
◆ Tel.:+351 265107979 ◆ [www.globalnavy.net](http://www.globalnavy.net) ◆ email: [sales@globalnavy.net](mailto:sales@globalnavy.net)