GlobalDur GN120 Epoxy Resin



TECHNICAL DATA SHEET

Epoxy Resin Solvent Free for Concrete

PRODUCT DESCRIPTION

- ♦ GlobalDur GN120ER is an excellent epoxy primer solvent free for Concrete.
- ◆ GlobalDur GN120ER is specially design to have excellent chemical resistance, mechanical and aesthetic properties.

PERFORMANCES

- Excellent adhesion to concrete.
- Excellent mechanical properties on mortars and glass reinforced fiber glass.
- No harmful solvents- Solvent free.
- Excellent wet ability to the substrates.
- · High mechanical properties.

RECOMMENDED USE

PRIMER/INTERMEDIATE/FINISH

OVER CONCRETE

Glossy.

MARINE: Decks, Chain lockers, Tower bridge, etc.

PROTECTIVE: Fiber glass reinforced laminates. Suitable for direct application on exterior and interior water pipes lines. Sewer lines. Dams and Concrete locks, primer on concrete water tanks, Fuel or Grains storage tanks. Flooring primer and epoxy mortar. Tunnels, etc..

APPROVALS

GLOSS

COMPONENT A	COMPONENT B	COLOURS
GN120ER	H120ER	Clear.

Physical Properties

52555	5.557		
SOLIDS BY VOLUME	100 % (theoretical)		
VOC*	Max. 40g/L.		
FLASH POINT	> 100°C (> 221°F) Setaflash		
PERFORMANCE	Adhesion: >1.5 N/mm2 (cohesive rupture on concrete) (ISO4624)		
	Hardness Shore D: ~75 (7d/23°C) (DIN53505)		
	Abrasion Resistance: 70 mg (7d/23°C) (CS10/1000/1000; ISO7784-2)		

Application

SURFACE PREPARATION

Painting Direct to Substrate: GlobalDur GN120ER is suitable for concrete surfaces prepared accordingly with NACE Nº6/SSPC-SP13 using:

Mechanical Surface Preparation Methods.

Chemical Surface Preparation Flame Cleaning and Blasting

Over coated surfaces be sure of the old coating conditions (no coating defects and corrosion- in

ISSUED Edition 03 / Mod.10 - 22/08/2017

GlobalDur GN120 Epoxy Resin



PERFORMANCE IN COATINGS

"sound conditions") and the c	compatibility with the GlobalDur	GN120ER. Please contact
GlobalNavy office in case of a	ny doubt or for further informat	tion.

APPLICATION METHOD

CONVENTIONAL METHODS: Due to the short pot-life of the product, brush and roller are suitable. Care should be taken in order to achieve the dft specified. When applying on enclosed areas ensure a good ventilation.

APPLICATION CONDITIONS

The substrate temperature shall be 10° -+ 50° C. The ambient temperature shall be > 10° C . The concrete moisture should be lower than 4%. Surface temperature must always be a minimum of 3°C (5°F) above dew point.

APPLICATION DATA

GlobalDur GN120ER Epoxy Resin is a two pack product, so the base and hardener must be mixed on the right ratio. First, mix well component A during 1 minutes. After that, add all the hardener and stir very well until it get homogeneous. Mix completely both quantities of component A and B packs.

MIX RATIO	2,2 / 1 (by Weight)	2 / 1 (by Volume)
-----------	---------------------	-------------------

HARDENER H120ER

POT LIFE 45 minutes (23°C/73°F).

THINNER GN008TH

SOLVENT / CLEANER GN008TH / GN003TH

DRY TIME Surface dry: 4 hours at 23°C (73°F).

Dry to recoat: Min: 12 hours at 23°C (73°F).

Max: 7 days at 23°C (73°F).

THEORETICAL COVERAGE

GN10ER: as primer for concrete 0 .22 Kg/sqm for 200 (8 mils) microns thickness.

TYPICAL PAINT SYSTEM

 GlobalDur GN120ER 1 x 0,15 Kg (dft) + GlobalDur GN132EFSL 1 x 0,40 Kg (dft). This is a system for flooring conditions. Please contact GlobalNavy for other applications.

STORAGE

4 years (storage on the original tightly closed containers in a dry, cool, well ventilated space, at temperatures between 5°C - 40°C).

PACKING

Two pack product, available in packs (A+B) 8 Kg and 21 Kg.

FURTHER INFORMATION

The conventional air spray is only possible with well organize painting system, due to the short pot-life - Please contact our GlobalNavy office.

HEALTH SAFETY

Please take the necessary measures in order to accomplish the national laws and regulations regarding the environmental, health and safety at work. Please observe the safety information displayed on the container. Please refer to the Safety Data Sheet for detailed information on the health, safety hazards and precautions for the use of this product.

The information on this data sheet is given to the best of our knowledge based on laboratory testing and practical experience. This is not a specification and all information is given in good faith. Every values presented as Theoretical were calculated from the product formula, so can have deviation from laboratory measurements using standard methods that may be not applicable. However, since the product can be used under conditions beyond our control, the manner of use is the sole responsibility of the user. The product is intended for professional use only. Manufacturer does not assume any liability in connection with the use of the product relative to coverage, performance or injury. This Technical Data Sheet content can be changed without notice.

Parque Industrial de Carrascas, Estrada Nacional 252, 2950-402 Palmela PORTUGAL

◆ Tel.:+351 265107979

♦ www.globalnavy.net
♦ email: sales@globalnavy.net

GlobalDur GN120 Epoxy Resin

