



# TECHNICAL DATA SHEET

## Epoxy Novolac Primer Converter and Moisture Tolerant

<b>PRODUCT DESCRIPTION</b>	<ul style="list-style-type: none"> <li>◆ GlobalDur GN133EN is an excellent epoxy novolac/amine two pack anticorrosion primer/finish for steel. Can also be applied over concrete.</li> <li>◆ GlobalDur GN133EN is specially designed to have high chemical resistance.</li> <li>◆ GlobalDur GN133EN is a primer specially designed for excellent chemical resistance performances at high temperatures.</li> <li>◆ GlobalDur GN133EN can be applied as a primer, intermediate or finish (however may have slight colour differences due to its particular properties).</li> </ul>	
<b>PERFORMANCES</b>	<ul style="list-style-type: none"> <li>• Excellent anticorrosive performance club with high chemical resistance;</li> <li>• No humidity/dew point restrictions;</li> <li>• Excellent resistance to wearing and impact;</li> <li>• Excellent anticorrosive properties at high temperatures;</li> <li>• Excellent adhesion to substrate and between coats;</li> <li>• Surface preparation cost reduction;</li> <li>• Excellent edge retention.</li> </ul>	
<b>RECOMMENDED USE</b>	<p>PRIMER/INTERMEDIATE/FINISH OVER STEEL                  MARINE: ballast tanks, fuel/crude oil tanks, decks, bilge and void areas, double bottoms, rigs, offshore platforms, etc..                  PROTECTIVE: Tanks, machinery, railroad cars, metallic structures, lead and other coatings covered structures, interior/exterior of fuel and water pipe lines.</p>	
<b>APPROVALS</b>	Complies with ISO 12944-5, as being suitable for coating systems until C5-M.	
<b>COMPONENT A</b>	<b>COMPONENT B</b>	<b>COLOURS</b>
GN133EN	H133EN	GN133ENG7000 (Light Grey), GN133ENG3009 (Red Iron Oxide). For other colours, please contact GlobalNavy's office.

### Physical Properties

<b>GLOSS</b>	Gloss.
<b>SOLIDS BY VOLUME</b>	100 % (theoretical).
<b>VOC*</b>	<90 g/L.
<b>FLASH POINT</b>	> 100° C (> 77°F) Setaflash
<b>PERFORMANCE</b>	

### Application

<b>SURFACE PREPARATION</b>	Painting Direct to the Substrate: GlobalDur GN133EN is suitable for surfaces prepared by grit blasting, accordingly with the following standards: Grit Blasting: SA2 (ISO 8501-1:1988)
----------------------------	---

# GlobalDur GN133 Epoxy Novolac



PERFORMANCE IN COATINGS

Apart from the surface preparation method, the moisture tolerance of GlobalDur GN133EpoxyNovolac allow the surface to be washed with tap water before painting, ensuring a final lower salts level. By this way, it is possible to achieve a non visual standard SC2 (NACE 5 / SSPC-SP12). Over coated surfaces be sure of the old coating conditions (no coating defects and corrosion- in "sound conditions") and the compatibility with the GlobalDur GN133EN. Please contact GlobalNavy office in case of any doubt or for further information.

<b>APPLICATION METHOD</b>	SPRAY: Use air less spray. Use an equipment with a compressing 63:1 ratio, an inlet 4,5 bar pressure, allowing a 240-310 bar outlet pressure. A 0,019" or 0,0 23" tip is recommended. Conventional spray equipment only on special application conditions- contact GlobalNavy for more information. CONVENTIONAL METHODS: Brush and roller are suitable for "stripe-coat" and small areas, care should be taken in order to achieve the specified DFT. When applying on enclosed areas ensure a good ventilation. It is not necessary to use dehumidification equipment: GlobalDur GN133EN can be applied on dry or wet surfaces, even with 100% humidity and surface temperatures below the dew point.
<b>APPLICATION CONDITIONS</b>	The substrate temperature shall be between 15°-+40°C. The ambient temperature shall be >10°C.
<b>APPLICATION DATA</b>	GlobalDur GN133 EpoxyNovolac is a two pack product, so the base and hardener must be mixed on the right ratio. First, mix well component A during 2 minutes. After that, add all the hardener and stir very well until it get homogeneous. Only if necessary, for na application optimization adjustment, the product can be diluted until 5 % (v/v) with GN001TH. Mix completely both quantities of component A and B packs.
<b>MIX RATIO</b>	5,2 / 1 (by Weight) 3,3 / 1 (by Volume)
<b>HARDENER</b>	H133EN
<b>POT LIFE</b>	90 minutes (23°C).
<b>THINNER</b>	GN001TH / GN003TH
<b>SOLVENT / CLEANER</b>	GN003TH
<b>DRY TIME</b>	Surface dry: 3 hours at 23°C (73°F) Dry to recoat: Min: 6 hours at 23° C (73°F). Max: 5 days at 23°C (73°F).
<b>THEORETICAL COVERAGE</b>	6.7 Sq.m/Lt. (256,4 Sq.ft/US gal - Dry/Wet: 150 micron (6 mils).
<b>TYPICAL PAINT SYSTEM</b>	• GlobalDur GN133EN 2 x 200µm (DFT). This is a system for immersion conditions. Please contact GlobalNavy for other applications.
<b>STORAGE</b>	4 years (storage on the original tightly closed containers in a dry, cool, well ventilated space, at temperatures between 5°C - 40°C).
<b>PACKING</b>	Two pack product, available in packs (A+B) 5 L and 20 L.
<b>FURTHER INFORMATION</b>	The conventional air spray is only possible with a much higher dilution ratio, so it only should be used on special applications - Please contact our GlobalNavy's office. For further chemical resistance see "Chemical Ressitance Table".
<b>HEALTH SAFETY</b>	Please take the necessary measures in order to accomplish the national laws and regulations regarding the environmental, health and safety at work. Please observe the safety information displayed on the container. Please refer to the Safety Data Sheet for detailed information on the health, safety hazards and precautions for the use of this product.

The information on this data sheet is given to the best of our knowledge based on laboratory testing and practical

## **GlobalDur GN133 Epoxy Novolac**



PERFORMANCE IN COATINGS

experience. This is not a specification and all information is given in good faith. Every values presented as Theoretical were calculated from the product formula, so can have deviation from laboratory measurements using standard methods that may be not applicable. However, since the product can be used under conditions beyond our control, the manner of use is the sole responsibility of the user. The product is intended for professional use only. Manufacturer does not assume any liability in connection with the use of the product relative to coverage, performance or injury. This Technical Data Sheet content can be changed without notice.

Parque Industrial de Carrascas, Estrada Nacional 252, 2950-402 Palmela PORTUGAL  
◆ Tel.:+351 265107979 ◆ [www.globalnavy.net](http://www.globalnavy.net) ◆ email: [sales@globalnavy.net](mailto:sales@globalnavy.net)