

GlobalThane GN202AM Polyurethane



PERFORMANCE IN COATINGS

TECHNICAL DATA SHEET

Polyurethane AntiMicrobial Satin Finish

PRODUCT DESCRIPTION	◆ GlobalThane GN202AMPF is an excellent weathering resistance two pack polyurethane finish. ◆ GlobalThane GN202AMPF is a special finish coating with antimicrobial properties. ◆ GlobalThane GN202PF has a satin finish.	
PERFORMANCES	<ul style="list-style-type: none">• Effective on suppressing the growth of algae, mold, mildew, fungi and bacteria;• Excellent colour retention;• Excellent glossy finish and easy to apply;• Excellent impact and abrasion resistance;• Good chemical resistance;• Good adhesion between coats.	
RECOMMENDED USE	FINISH OVER STEEL MARINE: Cabins, bathrooms, kitchens, etc.. PROTECTIVE: Interior of pipe lines, etc.. FINISH OVER CONCRETE FLOORING: Kitchens, toilets and bathrooms, hospital and clinic, etc.. FINISH OVER OTHER SUBSTRATES Recommended for application on Aluminium, Wood and Fiberglass, when properly primed.	
APPROVALS	Complies with EU Directive 2010/42/EC: subcategory j (VOC< 500 g/l). Complies with ISO 12944-5, as being suitable for coating systems until C5-M.	
COMPONENT A	COMPONENT B	COLOURS
GN202AMPF	H200P	GN202AMPFG9003 (White), GN202AMPFR7035 (light grey) GN202AMPFG9005 (Black). For other colours, please contact GlobalNavy's office.

Physical Properties

GLOSS	Satin.
SOLIDS BY VOLUME	50 ± 2 %
VOC*	< 500g/L.
FLASH POINT	>47°C (> 117°F) Setaflash

PERFORMANCE

Application

SURFACE PREPARATION	All the surfaces have to be clean, dry and without contamination. The surface should be evaluated and treated accordingly with ISO8504. Coated Surface: Clean, undamaged and dry compatible primer. Contact GlobalNavy office for more information.
----------------------------	--

ISSUED	Edition 03 / Mod.10 - 21/05/2018
---------------	----------------------------------

GlobalThane GN202AM Polyurethane



PERFORMANCE IN COATINGS

Other Surfaces: Check the suitability of GN202AMPF, apply a suitable primer following its Technical Data Sheet and then apply the GN202AMPF. Contact GlobalNavy office for further information.

APPLICATION METHOD	SPRAY: Use air less spray. Use an equipment with a 170-200 bar outlet pressure. A 0,012" - 0,017" tip is recommended. On conventional air spray equipment, it is advisable to use a pressure vessel adding the less possible thinner. CONVENTIONAL METHODS: Brush is suitable for "stripe-coat" and small areas; roller is suitable for flooring applications- care should be taken in order to achieve the specified DFT. When applying on enclosed areas ensure a good ventilation with dehumidified air.
APPLICATION CONDITIONS	The substrate temperature should be minimum 10°C (32°F) and at least 4°C (7°F) above the dew point of the air, measured in the vicinity of the surface. The moisture should be < 85%. Assure a good ventilation with dry air in confined areas.
APPLICATION DATA	GlobalThane GN202 Polyurethane Finish, is a two pack product, so the base and hardener must be mixed on the right ratio. First, mix well component A during 1 minute. After that, add all the hardener and stir very well until it get homogeneous. If necessary, for an application optimization adjustment, the product can be diluted until 10 % (v/v) with GN010TH. Mix completely both quantities of component A and B packs. Low temperature cause higher pot life, and higher temperatures decrease mixture pot life.
MIX RATIO	4 / 1 (by Weight) 3 / 1 (by Volume)
HARDENER	H200P
POT LIFE	4 hours (23°C/73°F).
THINNER	GlobalThyn GN010TH.
SOLVENT / CLEANER	GlobalThyn GN010TH.
DRY TIME	Surface dry: 3 hours at 23°C (73°F); 2 hour at 30°C (86°F). Dry to recoat: Min: 16 hours at 23°C (73°F).
THEORETICAL COVERAGE	10,0 m2/Lt (407 Sq.ft/US gal) Dry: 50 µm (2 mils) • Wet: 100 µm (4mils).
TYPICAL PAINT SYSTEM	• GlobalDur GN120ER 1 x 200g (DFT) • GlobalDur GN132EFSL 1 x 300g (DFT) • GlobalThane GN202MPFP 1 x 130g (WFT). This is a typical system for flooring conditions. Please contact GlobalNavy for other applications. If exact colour matching is required, ensure that GN202PF in each area is applied from the same control batch numbers.
STORAGE	4 years (storage on the original tightly closed containers in a dry, cool, well ventilated space, at temperatures between 5°C - 40°C).
PACKING	Two pack product, available in packs (A+B), 1L, 5 L and 20 L.
FURTHER INFORMATION	For the safety of the applicator and the good performance, ventilation should be provided to all portions of the enclosed area. Dry air IS VERY IMPORTANT. Product CAN NOT be applied with humidity over 85%.
HEALTH SAFETY	Please take the necessary measures in order to accomplish the national laws and regulations regarding the environmental, health and safety at work. Please observe the safety information displayed on the container. Please refer to the Safety Data Sheet for detailed information on the health, safety hazards and precautions for the use of this product.

The information on this data sheet is given to the best of our knowledge based on laboratory testing and practical

GlobalThane GN202AM Polyurethane



PERFORMANCE IN COATINGS

experience. This is not a specification and all information is given in good faith. Every values presented as Theoretical were calculated from the product formula, so can have deviation from laboratory measurements using standard methods that may be not applicable. However, since the product can be used under conditions beyond our control, the manner of use is the sole responsibility of the user. The product is intended for professional use only. Manufacturer does not assume any liability in connection with the use of the product relative to coverage, performance or injury. This Technical Data Sheet content can be changed without notice.

Parque Industrial de Carrascas, Estrada Nacional 252, 2950-402 Palmela PORTUGAL
◆ Tel.:+351 265107979 ◆ www.globalnavy.net ◆ email: sales@globalnavy.net