

GlobalThane GN206 PF Anti-Graffiti



TECHNICAL DATA SHEET



High Solids Polyurethane Finish Anti-Graffiti

PRODUCT DESCRIPTION	<ul style="list-style-type: none"> ◆ GlobalThane GN206PFAG is an excellent high solids two pack polyurethane finish. ◆ GlobalThane GN206PFAG is designed to have extremely low superficial tension in order to be difficult recoatability and anti stain (keeps your coating gloss and clean on harsh environments). ◆ GlobalThane GN206PFAG is a high glossy weathering resistance polyurethane finish. 	
PERFORMANCES	<ul style="list-style-type: none"> • Excellent cleaning efficiency, anti stain and hydrophobicity. • Excellent gloss and colour retention; • Excellent glossy finish and easy to apply; • High Solids; • Excellent anti-graffiti cleaning properties. 	
RECOMMENDED USE	<p>FINISH OVER STEEL AND CONCRETE MARINE: Offshore structures, chimneys, etc.. PROTECTIVE: Bridges, walls, chimneys, machinery, railroad cars, metallic structures, exterior of pipe lines. FINISH OVER OTHER SUBSTRATES Recommended for application on Aluminium, Wood and Fiberglass, when properly primed.</p>	
APPROVALS	<p>Complies with ASTM D7089- Cleanability level I and EU Directive 2010/42/EC: subcategory j (VOC < 500 g/l). Complies with ISO 12944-5, as being suitable for coating systems until C5-M.</p>	
COMPONENT A	COMPONENT B	COLOURS
GN206PFAG	H200P	GN206PFAGG9003 (White), GN206PFAGG9005 (Black). For other colours, like RAL colours, please contact GlobalNavy's office.

Physical Properties

GLOSS	Glossy
SOLIDS BY VOLUME	65 % (theoretical) ± 2 %
VOC*	Max. 270g/Lt
FLASH POINT	> 24°C (> 75°F) Setaflash
PHYSICAL PROPERTIES	<p>Density: 1,2 g/cm³</p> <p>Coating System Properties (GN120ER/GN206PFAG) Adhesion - Pull Off (ASTM D4541) Dry surface: >50 Kg/cm² (MPa) (710 psi) (or >1,5 Kg/cm² (MPa) cohesive on the concrete) Adhesion- Tape test (ASTM D3359) Rate - 5B (between finish coat GN206PFAG and GN120ER) Abrasion Strength (ISO7784-2) 32 mg (1000 cycles / 1000 g / CS10) Barcol Resistance (ASTM D2583) 24</p>

GlobalThane GN206 PF Anti-Graffiti



Maximum Elongation (ISO/R 527) 2%
 Elasticity Modulus (ISO/R 527) 106,000 KgF/cm²
 Compressive Strength (ISO 844) 1.020 KgF/cm² (15,000 psi)
 Flexural Strength (ISO 178) 650 KgF/cm² (9245 psi.)
 Impact Resistance (EN ISO 6272) IR4
 Exterior Exposure (ASTM D1014) 2 years- (Chalking) (ASTM D659): Rate 1
 QUV (Using A340 & B313 bulbs) 2000 hours – (Chalking) (ASTM D659): Rate 0
 Absorption (ASTM D570) 0,1%
 Fire Reaction (EN 13501-1) Bfl-s1

Application

SURFACE PREPARATION	<p>All the surfaces have to be clean, dry and without contamination. The surface should be evaluated and treated accordingly with ISO8504.</p> <p>Coated Surface: Clean, undamaged and dry compatible primer. Contact GlobalThaneNavy office for more information.</p> <p>Other Surfaces: Check the suitability of GN206PFAG, apply a suitable primer following its Technical Data Sheet and then apply the GN206PFAG. Contact GlobalThaneNavy office for further information.</p>
APPLICATION METHOD	<p>SPRAY: Use air less spray. Use an equipment with a 170-200 bar outlet pressure. A 0,012" - 0,017" tip is recommended. On conventional air spray equipment, it is advisable to use a pressure vessel adding the less possible thinner. CONVENTIONAL METHODS: Brush and roller are suitable for "stripe-coat" and small areas, care should be taken in order to achieve the specified DFT. When applying on enclosed areas ensure a good ventilation with dehumidified air.</p>
APPLICATION CONDITIONS	<p>The substrate temperature should be minimum 0°C (32°F) and at least 4°C (39°F) above the dew point of the air, measured in the vicinity of the surface. The moisture should be <85%. Assure a good ventilation with dry air in confined areas.</p>
APPLICATION DATA	<p>Global GN206 Polyurethane Finish Anti-Graffiti is a two pack product, so the base and hardener must be mixed on the right ratio. First, mix well component A during 1 minute. After that, add all the hardener and stir very well until it get homogeneous. If necessary, for na application optimization adjustment, the product can be diluted until 10 % (v/v) with GN001TH. Mix completely both quantities of component A and B packs. Low temperature cause higher pot life, and higher temperatures decrease mixture pot life.</p>
MIX RATIO	4 / 1 (by Weight) 3 / 1 (by Volume)
HARDENER	H200P
POT LIFE	2 hours (23°C/73°F).
THINNER	GN001TH
SOLVENT / CLEANER	GN001TH/GN010TH
DRY TIME	<p>Surface dry: 2 hours at 23°C (73°F); 1 hour at 30°C (86°F).</p> <p>Dry to recoat: Min: 16 hours at 23°C (73°F).</p>
THEORETICAL COVERAGE	12,8 m ² /Lt (520,96 Sq.ft/US gal) - Dft: 50 µm (2 mils) • Wet: 78 µm (3 mils)
TYPICAL PAINT SYSTEM	<p>• GlobalDur GN150EW 1 x 125µm (DFT) • GlobalThane GN206PFAG 1 x 65µm (DFT). This is a typical system for wall structures on normal conditions. Please contact GlobalNavy for other applications.</p>

GlobalThane GN206 PF Anti-Graffiti



If exact colour matching is required, ensure that GN206PFAG in each area is applied from the same control batch numbers.

STORAGE

4 years (storage on the original tightly closed containers in a dry, cool, well ventilated space, at temperatures between 5°C - 30°C).

PACKING

Two pack product, available in packs (A+B) 1L, 5L and 20L.

FURTHER INFORMATION

The ventilation should be done with dehumidified air.

HEALTH SAFETY

Please take the necessary measures in order to accomplish the national laws and regulations regarding the environmental, health and safety at work. Please observe the safety information displayed on the container. Please refer to the Safety Data Sheet for detailed information on the health, safety hazards and precautions for the use of this product.

The information on this data sheet is given to the best of our knowledge based on laboratory testing and practical experience. This is not a specification and all information is given in good faith. Every values presented as Theoretical were calculated from the product formula, so can have deviation from laboratory measurements using standard methods that may be not applicable. However, since the product can be used under conditions beyond our control, the manner of use is the sole responsibility of the user. The product is intended for professional use only. Manufacturer does not assume any liability in connection with the use of the product relative to coverage, performance or injury. This Technical Data Sheet content can be changed without notice.

Parque Industrial de Carrascas, Estrada Nacional 252, 2950-402 Palmela PORTUGAL
◆ Tel.:+351 265107979 ◆ www.globalnavy.net ◆ email: sales@globalnavy.net