### GlobalDur GN150Epoxy Waterbased



# TECHNICAL DATA SHEET

## **Epoxy Waterbased Coating**

| PRODUCT DESCRIPTION | ♦ GlobalDur GN150EW is a  | epoxy water based epoxy paint Multiproposal for concrete.                                    |  |
|---------------------|---|--|--|
|                     | ♦ GlobalDur GN150EW is a  | coating with chemical resistance and superior washability.                                   |  |
|                     | ♦ GlobalDur GN150EW is a  | economic epoxy system glossy designed for application on flooring                            |  |
|                     | and walls.  |  |  |
|                     | ♦ GlobalDur GN150EW is su   | uitable also recoat architectural water based paints.  |  |
| PERFORMANCES        | • High Solids;  |  |  |
|                     | • Excellent impact resistance   | ce;  |  |
|                     | Excellent levelling proper  | ties;  |  |
|                     | <ul> <li>Low organic solvent odor</li> </ul>  | and no flamable risk during application and dry;   |  |
|                     | <ul> <li>Excellent aestetic effect;</li> </ul>  |  |  |
|                     | <ul> <li>Excellent washability;</li> </ul>  |  |  |
|                     | Good Abrasion resistance  | and flexibility;   |  |
|                     | Good chemical resistance  | to alkali, acid and petroleum products;  |  |
|                     | <ul> <li>Good adhesion over wet a</li> </ul>  | and dry concrete, over primer and between coats.   |  |
| RECOMMENDED USE     | PRIMER/INTERMEDIATE/FII   | NISH   |  |
|                     | OVER CONCRETE   |  |  |
|                     | PROTECTIVE: Internal Flooring and walls on industrial facilities, kitchens, laboratories, car |  |  |
|                     | parkings, power stations, w   | kings, power stations, warehouses, hospitals, etc., where washability and solvent resistance |  |
|                     | to degreasers are importan  | t.   |  |
| APPROVALS           | Complies with ELL Directive   | 2010/42/EC: subcategory j (VOC< 140 g/l).  |  |
|                     | complies with LO Directive  | 2010/42/LC. Subcategoly J (VOC 140 g/l).   |  |
| COMPONENT A         | COMPONENT B   | COLOURS  |  |
| GN150EW             | H150EW  | GN150EWG9003 (White), GN150EWG9005 (Black), RAL colours. For                                 |  |
| L                   |   | other colours catalogue, please contact GlobalNavy's office.                                 |  |

#### **Physical Properties**

| GLOSS               | Glossy.                              |
|---------------------|--------------------------------------|
| SOLIDS BY VOLUME    | 85 ±2% (Volume).<br>90 ±2% (weight). |
| VOC*                | <100g/L.                             |
| FLASH POINT         | 101°C (214°F) Setaflash.             |
| PHYSICAL PROPERTIES | Density: 1,5 g/cm <sup>3</sup>       |
| Application         |                                      |

| SURFACE PREPARATION | All the surfaces has to be clean, dry and without contamination. The surface should be evaluated |  |
|---------------------|--|--|
|                     | and treated accordingly with ISO 8504.   |  |

ISSUED | / 38 / 02 / EN / 01-02-2024

# GlobalDur GN150Epoxy Waterbased



|                        | Coated Surface: Clean, undamaged and dry compatible primer.<br>Other Surfaces: Check the suitability of GN150EW, apply a suitable primer following its Technical<br>Data Sheet and then apply GN150EW. Contact GlobalNavy office for further information.   |  |  |
|------------------------|---|--|--|
| APPLICATION METHOD     | GlobalDur GN150EW can be applied by squeege, roller, brush.<br>Air-less spray:Use an equipment with a compressing 45:1 ratio, an inlet 3 bar pressure, allowing a<br>210-260 bar outlet pressure. A 0,019" or 0,0 21" tip is recommended. Conventional spray<br>equipment only on special application conditions- contact GlobalNavy for more information.  |  |  |
| APPLICATION CONDITIONS | The substrate temperature shall be 10°-+50°C. The ambient temperature shall be >10°C. Do not apply GN150EW with Humidity higher than 80%. In case of applying GN150EW as primer can be thin with 5% of water or GN008TH. When applying as intermediate or finish thin with water for orange peel surface or with GN008TH until 10% in all coats in order to achieve a better levelling surface.   |  |  |
| APPLICATION DATA       | GlobalDur GN150EW is a two pack product, so both components must be mixed on the right<br>ratio. Mix only using electrical mixer. First, component A should be well mixed during 2 minutes.<br>After that, add component B and stir very well until it get homogeneous. Only after that the<br>water/thinner should be add and continousely mixed. If over agitated, Pot Life will be reduced.<br>High temperatures will reduce Pot Life and Low temperatures will increase Pot Life. |  |  |
| MIX RATIO              | 3 / 1 (by weight) and 1.8 / 1 (by volume)   |  |  |
| HARDENER               | H150EW  |  |  |
| POT LIFE               | 1 hour at 23°C (73°F).  |  |  |
| THINNER                | Water / GN008TH   |  |  |
| SOLVENT / CLEANER      | GlobalThin GN003TH / GN008TH.   |  |  |
| DRY TIME               | Surface dry: Approx. 6 hours at 23°C (73°F) and 50% Rh;<br>Recoat: Min: 16 hours at 23°C (73°F)); Max: 7 days at 23°C (73°F). After that surface must e<br>reactivated with solvents or clean with HP water.<br>For foot traffic/Loading: 16h / 2 days.<br>For Chemical Resistance : 7 days.  |  |  |
| THEORETICAL COVERAGE   | 3.0 Sq.m/Kg for a 200 microns DFT. (333 grams wet by sqm -14 Sq.ft/ Lb.).   |  |  |
| TYPICAL PAINT SYSTEM   | • Primer (dry/wet concrete) GlobalDur GN 151EW 1 x 240g (WFT); • Finish GlobalDur GN 150EW 2 x 333 g (WFT).   |  |  |
| STORAGE                | 2 years (storage on the original tightly closed containers in a dry, cool, well ventilated space, at temperatures between $5^{\circ}$ C - $30^{\circ}$ C).  |  |  |
| PACKING                | Two pack product, available in packs (A+B) of 5 Kg and 30 Kg.   |  |  |
| FURTHER INFORMATION    | For the safety of the applicator and the good performance, ventilation should be provided to all portions of the enclosed area.<br>If exact colour matching is required, ensure that GN150EW in each area is applied from the same control batch numbers.   |  |  |
| HEALTH SAFETY          | Please take the necessary measures in order to accomplish the national laws and regulations regarding the environmental, health and safety at work. Please observe the safety information displayed on the container. Please refer to the Safety Data Sheet for detailed information on the health, safety hazards and precautions for the use of this product.   |  |  |

ISSUED | / 38 / 02 / EN / 01-02-2024

# GlobalDur GN150Epoxy Waterbased



The information on this data sheet is given to the best of our knowledge based on laboratory testing and practical experience. This is not a specification and all information is given in good faith. Every values presented as Theoretical were calculated from the product formula, so can have deviation from laboratory measurements using standard methods that may be not applicable. However, since the product can be used under conditions beyond our control, the manner of use is the sole responsibility of the user. The product is intended for professional use only. Manufacturer does not assume any liability in connection with the use of the product relative to coverage, performance or injury. This Technical Data Sheet content can be changed without notice.

Parque Industrial de Carrascas, Estrada Nacional 252, 2950-402 Palmela PORTUGAL ♦ Tel.:+351 265107979 ♦ www.globalnavy.net ♦ email: sales@globalnavy.net

ISSUED 1/38/02/EN/01-02-2024